

AFEX™ Natural Oil Polyols Tung Oil - Linseed Oil - Canola Oil (TLC) Series TLC10C, TLC15C, TLC20C, TLC23C, TLC30C

DESCRIPTION

- Natural oil polyol based on tung oil, linseed oil and canola oil
- Hydroxyl functionality of 1.0 - 3.0 and high/low molecular weight
- Contains three crosslinkable conjugated double bonds
- Compatible with various commercial polyols
- Soluble in various organic solvents
- Reacts with isocyanates, melamines, anhydrides and oxygen

APPLICATION

- Coatings, adhesives, sealants and elastomers (CASE)
- Crosslinkable waterborne polyurethane dispersions
- Waterborne or solvent-based melamine coatings and adhesives
- Potential crosslinking or curing agent for epoxy adhesives or coatings
- Polyurethane foam
- Special chemical or additives based on urethane chemistry

PERFORMANCE

AFEX™ polyols with low molecular weight and high functionality

- Increased crosslinking density
- Increased cohesive density
- Increased Modulus

AFEX™ polyols with high molecular weight and low functionality

- Increased elongation
- Improved low temperature resistance
- Increased peel strength

	TLC10C	TLC15C	TLC20C	TLC23C	TLC30C
Appearance	Transparent Liquid	Transparent Liquid	Transparent Liquid	Transparent Liquid	Transparent Liquid
Color (Gardner)	8 - 10	8 - 10	8 - 10	8 - 10	8 - 10
Odor	Mild Oil	Mild Oil	Mild Oil	Mild Oil	Mild Oil
Visc. Cps /RT	< 1000	< 1000	< 1000	< 1000	< 1000
Weight / Gal.	~ 8.2	~ 8.2	~ 8.2	~ 8.2	~ 8.2
Non-volatile, %	100	100	100	100	100
Equiv. Wt. On OH	663	354	199	148	295
Hydroxyl Number	85	159	282	380	190
Molecular Weight	663	531	399	333	885
Functionality	1	1.5	2	2.3	3
Moisture %	0.01 max	0.01 max	0.01 max	0.01 max	0.01 max

Patents pending

NONWARRANTY – The information and recommendations made herein are based on our own research and / or the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our products. Purchasers should make their own tests to determine the suitability of such products for their practical purposes. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents.