

LINE-A-LASTIC BUTYL RUBBER SOLUTIONS

LINE-A-LASTIC butyl rubber solutions consist of butyl rubber and mineral spirits. These products range in solids from 25% to 60% and are available at various viscosities. Specific custom blends of butyl rubber in conjunction with: polyisobutylene, amorphous polypropylene, polybutene and resins in the solvent vehicle of your choice are also available.

LINE-A-LASTIC butyl rubber solutions provide sealant and adhesive manufacturers with reductions in labor, machine, and adjustment time.

PRODUCT	SOLIDS +/-2	VISCOSITY CPS.	WT./GA L	COLOR	FLASH PT.
AL-8010	25%	80,000-150,000	6.79	AMBER	105F TCC
AL-8011	30%	100,000-210,000	6.8	AMBER	105F TCC
AL-8015	40%	350,000-600,000	6.9	AMBER	105F TCC
AL-8017	50%	1,200,000-2,000,000	7.1	AMBER	105F TCC
AL-8017-P	50%	300,000-650,000	7.1	AMBER	105F TCC
AL-8019-P	60%	300,000-600,000	7.18	AMBER	105F TCC

Viscosity testing is performed at 78F.

APPLICATION: **LINE-A-LASTIC** butyl rubber solutions are recommended primarily for compounding into high quality butyl rubber caulks, specifically those that meet U.S. and Canadian government specifications.

PACKAGING: These products are supplied in open top drums to provide the most convenient form of handling