2781500 AL-1150C 15% CPO CONCENTRATE

AL-1150C 15% is a water reducible adhesion promoter emulsion containing a phenolic resin modified chlorinated polyolefin (CPO). **AL-1150C** 15% is designed to be used where adhesion to polypropylene based substrates (PP & TPO) is necessary. **AL-1150C** 15% can be used as the main component of a water based adhesion promoter / primer or as an additive to one coat paint or adhesive systems. Gasoline and water resistance is improved when using **AL-1150** 15%.

TYPICAL PROPERTIES:

Total Weight Solids, %: 18 - 20

CPO Resin Solids, % 15

Lbs./Gallon 8.5

pH 9.0 - 10.0

Viscosity Zahn #1 22 - 26 seconds

APPLICATION:

Adhesion Promoter / Primer: Reduce with DI or RO water to desired weight solids (5-7%) Add additional fillers, co-resins and rheology modifiers to obtain viscosity and performance requirements. Air dry at room temperature or force dry at 180F for 5 minutes before applying subsequent coatings. Best adhesion results over TPO or PP are obtained when the adhesion promoter / primer is baked at elevated temperatures (180°-250°F for a minimum of 5 minutes).

Paint or Adhesive Additive: Add at (10-30%) by weight to water based paints or adhesives to provide adhesion for one-coat systems. Adjust AL-1150C 15% levels to obtain desired adhesion.

Manufactured under the following U.S. Patents, foreign patents pending. 5,227,198 5,300,363 5,427,856 5,620,747 5,626,915 5,629,046 5,693,423 5,756,566 5,804,640 5,880,190

Revised 10/26/10



Nonwarranty – The information and recommendations made herein are based on our own research and / or the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our products. Purchasers should make their own tests to determine the suitability of such products for their practical purposes. Nothing contained herein shall be construed to be a recommendation to user or as a license to operate under or to infringe any existing patents.

www.a-line.com