## AQUAPRIME Flexible Waterborne Primer Surfacer

#### **Description:**

AquaPrime is a flexible waterborne primer-surfacer designed for use on plastic body substrates including bumpers, grills, spoilers, valances, and body panels. The high solids of AquaPrime provides excellent fill and build properties and is compatible with most basecoat/clearcoat products.

### **Technical Data:**

Weight Per Gallon, lbs: Reducer: V.O.C., lbs/gal Appearance: Solids, wt %: 10.0 Not required, ready to spray. 0.80 Low Gloss Black 44.0

### Substrates:

AquaPrime will adhere to a variety of unpainted surfaces including:

Sheet Molding Compound (SMC) Bulk Molding Compound (BMC) Poly Vinyl Chloride (PVC) Polycarbonate (PC) Ethylene Propylene Diene Modified (PP/EPDM) Ethylene Propylene Modified (PP/EPM) Acrylonitrile Butadiene Styrene (ABS) Polyfenylene Oxide Polymer (PPO) Polyurethane (PUR)

# *Polypropylene (PP) or Thermal Polyolefin (TPO) substrates will <u>need to be coated</u> with an adhesion promoter before the application of AquaPrime Primer-Surfacer*

### **Application:**

Mix AquaPrime Flexible Primer- Surfacer well before using. This material is ready to use as received but can be reduced with distilled water to obtain lower spray viscosity.

- Surface to be coated should be thoroughly cleaned to remove any existing road film, dust, grease or any other dirt or surface contaminant. Dry surface before application.
- Spray apply 1 3 medium wet coats of AquaPrime.
- Flash dry for 5 minutes between coats
- Air dry for 1 to 2 hours
- Force dry for 40 minutes at 140° F

59001:2015 CERTIFIED 100 \*\*\*\*

**Nonwarranty** – The information and recommendations made herein are based on our own research and / or the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our products. Purchasers should make their own tests to determine the suitability of such products for their practical purposes. Nothing contained herein shall be construed to be a recommendation to user or as a license to operate under or to infringe any existing patents. 01/11/2013

www.a-line.com