

LINE-A-LASTIC BUTYL RUBBER SOLUTIONS

LINE-A-LASTIC butyl rubber solutions consist of butyl rubber and mineral spirits. These products range in solids from 25% to 60% and are available at various viscosities. Specific custom blends of butyl rubber in conjunction with: polyisobutylene, amorphous polypropylene, polybutene and resins in the solvent vehicle of your choice are also available.

LINE-A-LASTIC butyl rubber solutions provide sealant and adhesive manufacturers with reductions in labor, machine, and adjustment time.

PRODUCT	SOLIDS +/-2	VISCOSITY CPS.	WT./GA L	COLOR	FLASH PT.
AL-8010	25%	80,000-150,000	6.79	AMBER	105F TCC
AL-8011	30%	100,000-210,000	6.8	AMBER	105F TCC
AL-8015	40%	350,000-600,000	6.9	AMBER	105F TCC
AL-8017	50%	1,200,000-2,000,000	7.1	AMBER	105F TCC
AL-8017-P	50%	300,000-650,000	7.1	AMBER	105F TCC
AL-8019-P	60%	300,000-600,000	7.18	AMBER	105F TCC

Viscosity testing is performed at 78F.

APPLICATION: **LINE-A-LASTIC** butyl rubber solutions are recommended primarily for compounding into high quality butyl rubber caulks, specifically those that meet U.S. and Canadian government specifications.

PACKAGING: These products are supplied in open top drums to provide the most convenient form of handling



Nonwarranty - The information and recommendations made herein are based on our own research and / or the research of others and are believed to be accurate. However, nothing herein is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our products. Purchasers should make their own tests to determine the suitability of such products for their practical purposes. Nothing contained herein shall be construed to be a recommendation to user or as a license to operate under or to infringe any existing patents.

www.a-line.com